

TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



Applicant: Shanghai Langfeng Industrial Co., Ltd
Address: Room 910, Building 6, Luxiang Road 111, Shanghai, China
Contact Person: Jay Yuan

Sample Submitted: The Sample(s) and Its (Their) Information(s) Was (Were) Submitted by Applicant and Identified.

- A. Grey/Blue gloves (the whole gloves) - size 9/L - 9 pairs
- B. Light Blue thread - 1 piece
- C. Brown thread - 1 piece
- D. Black thread - 1 piece

Standard: EN 388:2016+A1:2018 & EN ISO 21420:2020
Colour: Grey/Blue
Style No.: LY3013

Product Specification:

Model	LY3013
Size	7-11
Glove Palm 1	Grey fabric coated with Blue latex
Back 1	Grey fabric with Black print
Cuff 1	Grey fabric with White elastic thread
Binding 1	Light Blue thread
Binding 2	Brown thread
Binding 3	Black thread

Sample Received Date: 2025-12-29 and 2026-01-12
Date of Testing: 2025-12-30 to 2026-01-14

Test Result(s): Refer to the Section 3 and 4

Note:

(1) Each order is subject to acceptance of our [General Terms and Conditions](#) and the [TÜV SÜD Testing, Certification, Validation and Verification Regulation](#), in the version valid at the time the contract is concluded. For full version of above both documents, please visit the link to view.

(2) The results in this report are relevant only to the sample(s) tested.

(3) The test report shall not be reproduced except in full without the written approval of the laboratory.

(4) Disclaimer Measurement Uncertainty:

Unless otherwise stated, the decision rule for conformity reporting is based on Binary Statement for Simple Acceptance Rule (w=0) stated in ILAC-G8:09/2019 or CNAS-GL015:2022.

(5) The testing report without CMA stamp is not legally binding and could only be used as internal reference material for the applicant. It shall not be provided as a notarial certification.

Laboratory:
TÜV SÜD Certification and Testing
(China) Co., Ltd. Xiamen Branch
Testing Location: Xiamen
Form No.: TC_XMN_F_24.04 E
Rev:03
Effective Date:2024-10-23

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
Report.Softlines@tuvsud.com
Web: www.tuvsud.cn

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Xiamen Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China



TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



1. Test Sample Photo(s)



Sample A



Sample B

Laboratory:
TÜV SÜD Certification and Testing
(China) Co., Ltd. Xiamen Branch
Testing Location: Xiamen
Form No.: TC_XMN_F_24.04 E
Rev:03
Effective Date:2024-10-23

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
Report.Softlines@tuvsud.com
Web: www.tuvsud.cn

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Xiamen Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China




TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



Sample C



Sample D

Laboratory:
TÜV SÜD Certification and Testing
(China) Co., Ltd. Xiamen Branch
Testing Location: Xiamen
Form No.: TC_XMN_F_24.04 E
Rev:03
Effective Date:2024-10-23

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
Report.Softlines@tuvsud.com
Web: www.tuvsud.cn

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Xiamen Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China



TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



2. Identification of The Test Subject

Sample	Description	Remark
001	Grey fabric with Blue latex coating (palm)	Finished Product (A)
002	Grey fabric with Black print (back)	Finished Product (A)
003	Grey fabric (back)	Finished Product (A)
004	Grey fabric with White elastic thread (cuff)	Finished Product (A)
005	Light Blue thread (binding)	Semi-product (B)
006	Brown thread (binding)	Semi-product (C)
007	Black thread (binding)	Semi-product (D)

Laboratory:
TÜV SÜD Certification and Testing
(China) Co., Ltd. Xiamen Branch
Testing Location: Xiamen
Form No.: TC_XMN_F_24.04 E
Rev:03
Effective Date:2024-10-23

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
Report.Softlines@tuvsud.com
Web: www.tuvsud.cn

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Xiamen Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China



TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



3. Conclusion

No.	Test Parameter(s)	Conclusion
1.	Abrasion Resistance	Level 2
2.	Blade Cut Resistance (Index)	Level 1
3.	Tear Strength	Level 4
4.	Puncture Resistance	Level 3
5.	Sizing and Measurement of Gloves	Pass
6.	Dexterity	Level 5
7.	Azo-Dye Test	Pass
8.	pH Value Test	Pass
9.	Polycyclic Aromatic Hydrocarbons (PAHs) Content Test	Pass

Notes: Pass = Meet Requirement Fail = Below Requirement
= No Comment - = Did Not Perform
N/A = Not Applicable

Remark: (1) Samples are tested as received.

TÜV SÜD Certification and Testing (China) Co., Ltd. Xiamen Branch

Reviewed by:

Stacey Yang
Softlines Department



Approved by:

Damon Zheng
Softlines Department

Nemo Chen
Softlines Department

Laboratory:
TÜV SÜD Certification and Testing
(China) Co., Ltd. Xiamen Branch
Testing Location: Xiamen
Form No.: TC_XMN_F_24.04 E
Rev:03
Effective Date:2024-10-23

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
Report.Softlines@tuvsud.com
Web: www.tuvsud.cn

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Xiamen Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China



TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



4. Test Results

4.1 Abrasion Resistance (EN 388:2016+A1:2018 Clause 4.1 & 6.1)

Pressure: (9.0±0.2) kPa

Adhesive tape: 3M™ Scotch

Abrasive paper: Klingspor PL31B, Grit 180

Sample	Position	Parameters	Results (rubs)	Requirement	Classification
A	Palm	Specimen 1	>500	/	/
		Specimen 2	>500		
		Specimen 3	>500		
		Specimen 4	>500		
		The lowest of the above values	>500	*	Level 2

Remark: * =

Performance level	1	2	3	4
Number of rubs	100	500	2,000	8,000

4.2 Blade Cut Resistance (Index) (EN 388:2016+A1:2018 Clause 4.1 & 6.2)

Blade: OLFA RB45

Cotton Canvas: n° 14861

Sample	Position	Specimen	Sequence	Control specimen C _n	Test specimen T	Control specimen C _{n+1}	Index I	Requirement	Classification	
A	Palm	Specimen 1	1	1.2	1.7	1.2	2.42	/	/	
			2	1.2	1.7	1.3	2.36			
			3	1.3	1.6	1.3	2.23			
			4	1.3	1.7	1.3	2.31			
			5	1.3	1.7	1.5	2.21			
			Final Index Value				2.31			
		Specimen 2	1	1.1	1.2	1.2	2.04			
			2	1.2	1.2	1.2	2.00			
			3	1.2	1.2	1.2	2.00			
			4	1.2	1.6	1.2	2.33			
			5	1.2	1.4	1.2	2.17			
			Final Index Value				2.11			
			The lowest of the two calculated index values				2.11			*

Remark: * =

Performance level	1	2	3	4	5
index	1.2	2.5	5.0	10.0	20.0

Laboratory:
TÜV SÜD Certification and Testing
(China) Co., Ltd. Xiamen Branch
Testing Location: Xiamen
Form No.: TC_XMN_F_24.04 E
Rev:03
Effective Date:2024-10-23

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
Report.Softlines@tuvsud.com
Web: www.tuvsud.cn

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Xiamen Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China



TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



4.3 Tear Strength (EN 388:2016+A1:2018 Clause 4.1 & 6.4)

Sample	Position	Direction	Parameters	Results (N)	Requirement	Classification
A	Palm	Along cuff to fingertips	Specimen 1	>75	/	/
			Specimen 2	>75		
		Across the palm width	Specimen 1	>75		
			Specimen 2	>75		
		The lowest of the individual values				

Remark: *=

Performance level	1	2	3	4
Tear force (N)	10	25	50	75

4.4 Puncture Resistance (EN 388:2016+A1:2018 Clause 4.1 & 6.5)

Sample	Position	Parameters	Results (N)	Requirement	Classification	
A	Palm	The highest value of the force	Specimen 1	105.5	/	/
			Specimen 2	101.1		
			Specimen 3	107.2		
			Specimen 4	109.9		
		The lowest of the individual values				

Remark: *=

Performance level	1	2	3	4
Puncture resistance (N)	20	60	100	150

4.5 Sizing and Measurement of Gloves (EN ISO 21420:2020 Clause 5.1 & 6.1)

Sample	Size	Parameters	Results	Requirement	Conclusion
A	9/L	Fitting	Fit size 9	Sizes of gloves are defined with respect to the sizes of the hands they are to fit	Pass

4.6 Dexterity (EN ISO 21420:2020 Clause 5.2 & 6.2)

Sample	Specimen	Parameters	Results (mm)	Requirement	Classification
A	Specimen 1	The smallest diameter of the pin that can be picked up	5	/	/
	Specimen 2	The smallest diameter of the pin that can be picked up	5		
	Specimen 3	The smallest diameter of the pin that can be picked up	5		
	Specimen 4	The smallest diameter of the pin that can be picked up	5		
	The smallest diameter of the pin that can be picked up				

Remark: *=

Performance level	0	1	2	3	4	5
Smallest diameter of pin (mm)	No pin can be picked up	11.0	9.5	8.0	6.5	5

Laboratory:
TÜV SÜD Certification and Testing
(China) Co., Ltd. Xiamen Branch
Testing Location: Xiamen
Form No.: TC_XMN_F_24.04 E
Rev:03
Effective Date:2024-10-23

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
Report.Softlines@tuvsud.com
Web: www.tuvsud.cn

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Xiamen Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China



TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



4.7 Azo-Dye Test (EN ISO 21420:2020 Clause 4.2)

Test with reference to EN ISO 14362-1:2017- Textile materials

EN ISO 14362-3:2017- Textile materials (4-aminoazobenzene), determined by GCMS/HPLC-DAD

[Reporting Limit = 5.0 mg/kg]

No.	Substances List	CAS No.	Result (mg/kg)		Requirement (mg/kg)
			002	003	
1	4-Aminobiphenyl	92-67-1	ND	ND	<5
2	Benzidine	92-87-5	ND	ND	<5
3	4-Chloro-2-methylaniline	95-69-2	ND	ND	<5
4	2-Naphthylamine	91-59-8	ND	ND	<5
5	o-Aminoazotoluene	97-56-3	ND	ND	<5
6	5-Nitro-o-tolidine	99-55-8	ND	ND	<5
7	4-Chloroaniline	106-47-8	ND	ND	<5
8	2,4-diaminoanisole	615-05-4	ND	ND	<5
9	Bis-(4-aminophenyl)methane	101-77-9	ND	ND	<5
10	3,3'-Dichlorobenzidine	91-94-1	ND	ND	<5
11	3,3'-Dimethoxybenzidine	119-90-4	ND	ND	<5
12	o-tolidine	119-93-7	ND	ND	<5
13	3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	ND	ND	<5
14	2-Methoxy-5-methylaniline	120-71-8	ND	ND	<5
15	4,4'-Methylene bis(o-chloroaniline)	101-14-4	ND	ND	<5
16	4,4'-Oxydianiline	101-80-4	ND	ND	<5
17	4,4'-Thiodianiline	139-65-1	ND	ND	<5
18	o-tolidine	95-53-4	ND	ND	<5
19	2,4-Diaminotoluene	95-80-7	ND	ND	<5
20	2,4,5-Trimethylaniline	137-17-7	ND	ND	<5
21	o-Anisidine	90-04-0	ND	ND	<5
22	4-Amino-azobenzene	60-09-3	ND	ND	<5
23	2,4-Dimethylaniline	95-68-1	ND	ND	<5
24	2,6-Dimethylaniline	87-62-7	ND	ND	<5
25	4-chloro-o-toluidinium chloride	3165-93-3	ND	ND	<5
26	2-Naphthylammoniumacetate	553-00-4	ND	ND	<5
27	2,4-diaminoanisole sulphate	39156-41-7	ND	ND	<5
28	2,4,5-trimethylanilinehydrochloride	21436-97-5	ND	ND	<5
	Test Method	--	EN ISO 14362-1:2017(P1) EN ISO 14362-1:2017(P2)	EN ISO 14362-1:2017(P1) EN ISO 14362-1:2017(P2)	--
	Conclusion	--	Pass		--

- Remark:
1. ND = not detected (Less than Reporting Limit)
 2. mg/kg = milligram per kilogram
 3. "<" denotes less than
 4. P1=Direct reduction
 5. P2=Colorant extraction

Laboratory:
TÜV SÜD Certification and Testing
(China) Co., Ltd. Xiamen Branch
Testing Location: Xiamen
Form No.: TC_XMN_F_24.04 E
Rev:03
Effective Date:2024-10-23

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
Report.Softlines@tuvsud.com
Web: www.tuvsud.cn

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Xiamen Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China



TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



4.7 Azo-Dye Test (EN ISO 21420:2020 Clause 4.2)

Test with reference to EN ISO 14362-1:2017- Textile materials

EN ISO 14362-3:2017- Textile materials (4-aminoazobenzene), determined by GCMS/HPLC-DAD

[Reporting Limit = 5.0 mg/kg]

No.	Substances List	CAS No.	Result (mg/kg)		Requirement (mg/kg)
			005	006	
1	4-Aminobiphenyl	92-67-1	ND	ND	<5
2	Benzidine	92-87-5	ND	ND	<5
3	4-Chloro-2-methylaniline	95-69-2	ND	ND	<5
4	2-Naphthylamine	91-59-8	ND	ND	<5
5	o-Aminoazotoluene	97-56-3	ND	ND	<5
6	5-Nitro-o-toluidine	99-55-8	ND	ND	<5
7	4-Chloroaniline	106-47-8	ND	ND	<5
8	2,4-diaminoanisole	615-05-4	ND	ND	<5
9	Bis-(4-aminophenyl)methane	101-77-9	ND	ND	<5
10	3,3'-Dichlorobenzidine	91-94-1	ND	ND	<5
11	3,3'-Dimethoxybenzidine	119-90-4	ND	ND	<5
12	o-toluidine	119-93-7	ND	ND	<5
13	3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	ND	ND	<5
14	2-Methoxy-5-methylaniline	120-71-8	ND	ND	<5
15	4,4'-Methylene bis(o-chloroaniline)	101-14-4	ND	ND	<5
16	4,4'-Oxydianiline	101-80-4	ND	ND	<5
17	4,4'-Thiodianiline	139-65-1	ND	ND	<5
18	o-toluidine	95-53-4	ND	ND	<5
19	2,4-Diaminotoluene	95-80-7	ND	ND	<5
20	2,4,5-Trimethylaniline	137-17-7	ND	ND	<5
21	o-Anisidine	90-04-0	ND	ND	<5
22	4-Amino-azobenzene	60-09-3	ND	ND	<5
23	2,4-Dimethylaniline	95-68-1	ND	ND	<5
24	2,6-Dimethylaniline	87-62-7	ND	ND	<5
25	4-chloro-o-toluidinium chloride	3165-93-3	ND	ND	<5
26	2-Naphthylammoniumacetate	553-00-4	ND	ND	<5
27	2,4-diaminoanisole sulphate	39156-41-7	ND	ND	<5
28	2,4,5-trimethylanilinehydrochloride	21436-97-5	ND	ND	<5
	Test Method	--	EN ISO 14362-1:2017(P1) EN ISO 14362-1:2017(P2)	EN ISO 14362-1:2017(P1) EN ISO 14362-1:2017(P2)	--
	Conclusion	--	Pass		--

- Remark:
1. ND = not detected (Less than Reporting Limit)
 2. mg/kg = milligram per kilogram
 3. "<" denotes less than
 4. P1=Direct reduction
 5. P2=Colorant extraction

Laboratory:
TUV SUD Certification and Testing
(China) Co., Ltd. Xiamen Branch
Testing Location: Xiamen
Form No.: TC_XMN_F_24.04 E
Rev:03
Effective Date:2024-10-23

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
Report.Softlines@tuvsud.com
Web: www.tuvsud.cn

Regd. Office:
TUV SUD Certification and Testing (China) Co., Ltd.
Xiamen Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China



TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



4.7 Azo-Dye Test (EN ISO 21420:2020 Clause 4.2)

Test with reference to EN ISO 14362-1:2017- Textile materials

EN ISO 14362-3:2017- Textile materials (4-aminoazobenzene), determined by GCMS/HPLC-DAD

[Reporting Limit = 5.0 mg/kg]

No.	Substances List	CAS No.	Result (mg/kg)	Requirement (mg/kg)
			007	
1	4-Aminobiphenyl	92-67-1	ND	<5
2	Benzidine	92-87-5	ND	<5
3	4-Chloro-2-methylaniline	95-69-2	ND	<5
4	2-Naphthylamine	91-59-8	ND	<5
5	o-Aminoazotoluene	97-56-3	ND	<5
6	5-Nitro-o-toluidine	99-55-8	ND	<5
7	4-Chloroaniline	106-47-8	ND	<5
8	2,4-diaminoanisole	615-05-4	ND	<5
9	Bis-(4-aminophenyl)methane	101-77-9	ND	<5
10	3,3'-Dichlorobenzidine	91-94-1	ND	<5
11	3,3'-Dimethoxybenzidine	119-90-4	ND	<5
12	o-tolidine	119-93-7	ND	<5
13	3,3'-Dimethyl-4,4'-diaminodiphenylmethane	838-88-0	ND	<5
14	2-Methoxy-5-methylaniline	120-71-8	ND	<5
15	4,4'-Methylene bis(o-chloroaniline)	101-14-4	ND	<5
16	4,4'-Oxydianiline	101-80-4	ND	<5
17	4,4'-Thiodianiline	139-65-1	ND	<5
18	o-toluidine	95-53-4	ND	<5
19	2,4-Diaminotoluene	95-80-7	ND	<5
20	2,4,5-Trimethylaniline	137-17-7	ND	<5
21	o-Anisidine	90-04-0	ND	<5
22	4-Amino-azobenzene	60-09-3	ND	<5
23	2,4-Dimethylaniline	95-68-1	ND	<5
24	2,6-Dimethylaniline	87-62-7	ND	<5
25	4-chloro-o-toluidinium chloride	3165-93-3	ND	<5
26	2-Naphthylammoniumacetate	553-00-4	ND	<5
27	2,4-diaminoanisole sulphate	39156-41-7	ND	<5
28	2,4,5-trimethylanilinehydrochloride	21436-97-5	ND	<5
	Test Method	--	EN ISO 14362-1:2017(P1) EN ISO 14362-1:2017(P2)	--
	Conclusion	--	Pass	--

- Remark:
1. ND = not detected (Less than Reporting Limit)
 2. mg/kg = milligram per kilogram
 3. "<" denotes less than
 4. P1=Direct reduction
 5. P2=Colorant extraction

Laboratory:
TÜV SÜD Certification and Testing
(China) Co., Ltd. Xiamen Branch
Testing Location: Xiamen
Form No.: TC_XMN_F_24.04 E
Rev:03
Effective Date:2024-10-23

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
Report.Softlines@tuvsud.com
Web: www.tuvsud.cn

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd.
Xiamen Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China



TEST REPORT

Report No.: 66.430.26.0142.01

Dated: 2026-01-20



中国认可
国际互认
检测
TESTING
CNAS L7038



4.8 pH Value Test (EN ISO 21420:2020 Clause 4.2)

Test with reference to ISO 3071:2020, using KCl solution, determined by pH meter

Sample	Result	Requirement	Conclusion
001	6.6	3.5 < pH < 9.5	Pass
002	6.9	3.5 < pH < 9.5	Pass
004	6.8	3.5 < pH < 9.5	Pass
005	7.0	3.5 < pH < 9.5	Pass
006	6.9	3.5 < pH < 9.5	Pass
007	7.0	3.5 < pH < 9.5	Pass

Remark: 1. Temperature of the solution is 22.0°C during measurement
2. "<" denotes less than

4.9 Polycyclic Aromatic Hydrocarbons (PAHs) Content Test (EN ISO 21420:2020 Clause 4.2)

Test with reference to ISO 16190:2021, determined by GC-MS

[Reporting Limit = 0.10 mg/kg]

No.	Substances List	CAS No.	Result (mg/kg)	Requirement (mg/kg)
			001	
1	Benzo[a]pyrene	50-32-8	ND	Each <1
2	Benzo[e]pyrene	192-97-2	ND	
3	Benzo[a]anthracene	56-55-3	ND	
4	Benzo[b]fluoranthene	205-99-2	ND	
5	Benzo[j]fluoranthene	205-82-3	ND	
6	Benzo[k]fluoranthene	207-08-9	ND	
7	Chrysene	218-01-9	ND	
8	Dibenzo[ah]anthracene	53-70-3	ND	
Conclusion			Pass	--

Remark: 1. "mg/kg" denotes milligram per kilogram
2. "ND" denotes Not Detected
3. "<" denotes less than

-- END OF THE TEST REPORT --